



## FLEXPRO-HRV-S

A multipurpose thermoplastic elastomer for products or applications that require flexibility, durability and weather resistance.

---

### Processing Applications

Injection molding, extrusion, or other melt processing techniques.

---

### Product Descriptions

Form(s) Pellets  
Color Natural  
Handling 25 kg./bag

Property	Test method	Unit	Value
Shore Hardness (instantly)	ASTM D2240	Shore A	78
Shore Hardness (after 5S)	ASTM D2240	Shore A	71
Tensile strength	ASTM D638	MPa	12.02
Elongation at break	ASTM D638	%	934.98

---

### Key Features

- Soft rubber touch

Remark: 1.This grade need to dry before processing.  
2. Recommended processing conditions: Melt temperature: 180-220 °C



**Soul Best Co.,Ltd.**  
26/55, 2nd Floor, Nang Lin Chee Road, Thungmahamek, Sathorn,  
Bangkok 10120, Thailand  
Website: [www.soulbest.co.th](http://www.soulbest.co.th)  
Customer service tel: +66 8 9668 2165  
Email: [keerati.lak@soulbest.co.th](mailto:keerati.lak@soulbest.co.th)

---

#### Legal Disclaimer

The above information is believed to be accurate and is presented in good faith. However, since the conditions of application or use are outside our control, no warranty, either express or implied, is offered regarding the product, information or fitness for any particular purpose, or that the product or information may be used without infringing the intellectual property rights of others. SOUL BEST Co., Ltd. assumes no obligation or liability for the data or information given and such data and information are provided on condition that you accept full responsibility for all evaluation or investigation work necessary to determine the suitability of the product for use in your processes, and that such use will not infringe the intellectual property rights of others.